


Nufern 780 nm Select Cut-Off Single-Mode Fiber



Nufern's 780-HP high-performance select cut-off single-mode fiber is optimized at near IR wavelengths. This application-specific fiber was developed for applications requiring coupler generation, diode pigtails and unique delivery needs for the near IR continuum. Compared to the best fibers available today, 780-HP fiber features higher proof test levels and tighter second mode cut-off tolerance. These features result in higher strength, increased component reliability, improved production yields and reduced costs for component manufacturers.

Typical Applications

- Couplers
- Diode pigtails

Features & Benefits

- Superior fiber geometrical tolerances — Improved connectorization and coupling performance
- Extremely tight second mode cutoff tolerance — Enhanced component reproducibility
- Higher proof test level — Greater reliability for tight bend applications

Optical Specifications


Operating Wavelength (nominal)
 Mode Field Diameter (1/e² fit - near field)
 Second Mode Cut-Off
 Attenuation (nominal)
 Attenuation
 Numerical Aperture (nominal)
 Bend Loss for 100 turns @ 13 mm radius
 Bend Radius for 0.05 dB per 100 turns

780-HP

780 - 970 nm
 5.0 ± 0.5 μm @ 850 nm
 730 ± 30 nm
 4 dB/km @ 780 nm
 < 3.5 dB/km @850 nm
 0.13
 < 0.001 dB @ 780 nm
 Less than LTBR @ 780 nm

Geometrical & Mechanical Specifications

Clad Diameter 125.0 ± 1.5 μm
 Coating Diameter 245 ± 15 μm
 Core-Clad Concentricity < 0.5 μm
 Coating/Clad Offset ≤ 5 μm
 Coating Material UV Curable, Dual Acrylate
 Operating Temperature -55 to +85° C
 Short-Term Bend Radius ≥ 6 mm
 Long-Term Bend Radius ≥ 13 mm
 Proof Test Level ≥ 200 kpsi (1.4 GN/m²)



RoHS

7 Airport Park Road, East Granby, CT 06026 • 860.408.5000 • Toll-free 866.466.0214 • Fax 860.844.0210 E-mail info @ nufern.com • www.nufern.com

Standard specifications and design parameters are listed above. Specifications are subject to change without notice. Other configurations such as alternative form factors, optimized cut-off and UV cured color coating may be available. Let us know how Nufern can assist with your requirements.

NU0016-10/06